

## Neodur® Stone Varnish

**Transparent acrylic varnish,  
suitable for stones and stamped concrete**

### Description

Transparent, one-component, solvent-based pure-acrylic varnish, suitable for stones and stamped concrete. Ideal for the impregnation of porous surfaces, as well as for preventing dust generation in concrete floors. Contains UV filters.

### Fields of application

- Porous stones
- Stamped concrete
- Concrete floors to prevent dust generation

### Properties - Advantages

- Penetrates deep into the surface
- Contains UV filters, offering high resistance to solar radiation and yellowing
- Waterproofs and protects the surfaces from mould growth and atmospheric pollution
- Enhances the natural appearance of the surface
- Fast-drying



### Packing

200L, 20L, 4L and 1L

### Appearance

Transparent, satin

### Technical characteristics

Density (EN ISO 2811-1)	0,90kg/L (±0,05)
Adhesion strength (EN 13892-8)	≥2N/mm <sup>2</sup>

**Consumption: 120-140ml/m<sup>2</sup> for one layer (depending on the absorptivity of the substrate)**

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<70%
Application temperature (ambient - substrate)	+10°C min. / +35°C max.

### Curing details

Drying time (+25°C, RH 50%)	1 hour (initially)
Dry to recoat (+25°C, RH 50%)	3 hours

*\* Low temperatures and high humidity during application and/or curing prolong the above times, while high temperatures reduce them*

### Instructions for use

#### **Substrate preparation**

The surface must be stable, clean, dry, protected from rising moisture and free of dust, grease and loose materials. Any poorly adhering materials and older coatings should be thoroughly removed and the surface should be thoroughly cleaned, by proper mechanical or chemical means. Depending on the substrate, appropriate mechanical preparation may be required, in order to smooth out the irregularities, open the pores and create the optimum conditions for adhesion.

#### **Application**

**Neodur® Stone Varnish** is applied in one layer, undiluted, by roller, brush or airless spray. In surfaces of high porosity and increased absorptivity, higher consumption or an additional layer may be required.

### Special notes

- **Neodur® Stone Varnish** should not be applied under wet conditions, or if wet conditions or rainy weather are expected to prevail during the application or the curing period
- It should not be applied on surfaces where water repellent impregnation materials (e.g., siloxane-based) or waxes have been applied in the past

<b>Appearance (cured)</b>	Transparent, satin
<b>Packing</b>	20L, 4L and 1L in metal cans 200L in metal drums
<b>Cleaning of tools – Stains removal</b>	By <b>Neotex® 1021</b> immediately after application. In case of hardened stains, by mechanical means
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AhSB: 750g/l (Limit 1.1.2010) - V.O.C. content of the ready-to-use product <750g/l
<b>UFI code</b>	6E50-40RE-600A-HKG5
<b>Storage stability</b>	2 years, stored in its original sealed packing, protected from frost, humidity and exposure to sunlight



The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275

[www.neotex.gr](http://www.neotex.gr) ● [export@neotex.gr](mailto:export@neotex.gr)